

UNITED STATES PATENT APPLICATION FOR:

VERY THIN, LIGHT BIPOLAR PLATES

INVENTORS:

**Craig Andrews
Chris Boyer
Oliver J. Murphy
Al Cisar
Brad Fiebig**

CERTIFICATE OF MAILING BY EXPRESS MAIL

I hereby certify that this correspondence is being deposited with the United States Postal Service as Express Mail No. EV306376760US in an envelope addressed to Mail Stop Patent Application, Commissioner of Patents, PO Box 1450, Alexandria, VA 22313-1450, on the date as shown below.

Jeffrey L. Streets
Name of Registered Representative

Jeffrey L. Streets
Signature

December 4, 2003
Date of Signature

VERY THIN, LIGHT BIPOLAR PLATES

This application claims priority to U.S. Provisional Patent Application number 60/431,007 filed on December 4, 2002.

BACKGROUND OF THE INVENTION

5 Field of the Invention

The present invention relates to electrochemical cell components, and more specifically to separator plates within electrochemical cell stacks.

Description of Related Art

10 Electrochemical cells having proton exchange membranes (PEM) may be configured into electrochemical cell stacks. Each of the electrochemical cells in the stack are separated from adjacent cells with bipolar separator plates. These bipolar separator plates are typically made from a variety of metals, such as titanium and stainless steel, and from non-metallic conductors, such as graphitic carbon. Bipolar separator plates may
15 be fabricated by machining fluid flow fields into solid sheets of material. The flow fields typically comprise a series of channels or grooves that direct the flow of gases and liquids over the faces of the electrodes.

In a typical electrochemical cell, the membrane and electrode assembly (MEA) may be supported on either side by the fluid flow fields and the bipolar plate, and are
20 surrounded by cell frames that provide sealing surfaces and support. The cell frames have at least one manifold or flow passage, and often have several manifolds to direct the reactant and product fluid streams to their respective cathode or anode sides of the electrochemical cells. In a single cell arrangement, cell frames, flow fields and bipolar plates are provided on each of the anode and cathode sides.

25 The cell frames are usually sealed by means of sealing ridges, which are embossed, machined, or molded into the frame. The sealing features react against gaskets included in the stack to maintain fluid tight joints and also to grip the gaskets, which prevents creep and extrusion of the membrane. The electrochemical cell stack is conventionally placed under compressive forces by tie bars that are threaded through the
30 stack and apply compressive forces through the end plates at each end of the stack. The compression of the fuel cell stack applies the sealing force to the sealing surfaces

between the separator plates and membranes. Such seals typically circumscribe the manifolds and the electrochemically active area on the cell frame.

5 In addition to providing a fluid flow field and structural support for the MEA, a bipolar separator plate also collects electrons liberated at one electrode, conducts the electrons through the plate, and delivers electrons to the face of another electrode on the opposing side of the plate. In this manner, the bipolar plate acts as a current collector and therefore is usually constructed of a conductive material.

10 Conventional PEM electrochemical cells may have bipolar plates that are constructed from a variety of materials of construction depending on the service of the electrochemical cell stack and the corrosiveness of the reactants and products flowing through the stack. Often the bipolar plate may be fabricated from a solid sheet of material having the flow fields machined or stamped into the surface of the solid sheet. Alternatively, the bipolar plates may be formed in molds having flow fields included in the mold design.

15 Watkins, *et al.*, in U.S. Patent No. 5,108,849, issued April 28, 1992, discloses a fluid flow field plate made of a conducting material, preferably graphite. A fluid flow channel is machined, stamped or molded into the surface of the fluid flow field plate. The disclosed fluid flow plate has a fairly high density and lends considerably to the overall weight of an electrochemical cell stack.

20 Mercuri, *et al.*, in U.S. Patent No. 6,037,074, issued March 14, 2000, discloses a fluid flow field plate constructed of a graphite sheet impregnated with a resin and dispersed throughout with needle shaped ceramic fibers. A flow channel is stamped into one surface of the graphite sheet and the opposite surface is backed with a second graphite sheet to impart rigidity to the assembly.

25 It is apparent that the bipolar plates and cell frames contribute greatly to the bulk and weight of electrochemical cell stacks. Accordingly, there remains a need for bipolar plates having significantly less density so that the overall weight of the electrochemical cell stack may be reduced. It would be an advantage if the bipolar plate also had reduced dimensions, thereby further decreasing the weight of the electrochemical cell stack.

30

SUMMARY OF THE INVENTION

The present invention provides a bipolar plate having a fluid barrier and a sealing frame formed around a perimeter of the fluid barrier, wherein the frame is formed by injecting a polymer into a mold overlapping the perimeter of the fluid barrier. The fluid barrier may be a metal and may be selected from, for example, titanium, stainless steel, nickel, tantalum, niobium, and alloys thereof. The fluid barrier may be plated with a metal selected, for example, from gold, silver, copper, platinum, and combinations thereof. Alternately the fluid barrier may be an electrically conductive non-metal, such as a conductive polymer or metal filled polymer.

The bipolar plate may further comprise an anode flow field on a first side of the fluid barrier and a cathode flow field on the second side. The anode and cathode flow fields may be attached to the fluid barrier before the sealing frame is formed around the perimeter. Optionally, they may be attached after the sealing frame is formed. The flow fields may be attached to the fluid barrier by methods selected from, for example, adhesives, sintering, soldering and combinations thereof. Optionally, the flow fields may be etched into the fluid barrier. The flow fields may also be made of materials selected from, for example, expanded metal mesh, metal foam, conducting polymer foam, porous conductive carbon material and combinations thereof.

The bipolar plate may also include a first gasket to provide a sealing surface between a first side of the sealing frame and a first membrane and electrode assembly and a second gasket to provide a sealing surface between a second side of the sealing frame and a second membrane and electrode assembly. The gaskets may optionally be applied by print screening or the gaskets may be incorporated into the sealing frame.

The bipolar plate may further include components selected from alignment pins, alignment holes, reinforcing liners for fluid passages, fluid manifolds and combinations thereof, wherein the sealing frame is formed around the components.

The polymer used to form the frame may be selected from a thermoplastic, a thermoset, a reactive set and combinations thereof. Examples of suitable polymers include polyvinylidene fluoride, polyvinylidene difluoride, polytetrafluoroethylene, polyamides, polysulfone, polyetherketones, polycarbonate, polypropylene, polyimides, polyurethanes, epoxies, silicones, and combinations thereof. The polymer may be mixed

with a filler, such as organic polyamide fibers, to improve the characteristics of the polymer and modify the performance of the polymer. The filler may also act as a diluent.

The present invention further provides a bipolar plate comprising a gas barrier having a cathode side and an anode side, a cathode sealing frame adapted to receive a
5 perimeter of the cathode side of the fluid barrier, and an anode sealing frame adapted to receive a perimeter of the anode side of the fluid barrier, wherein the cathode sealing frame and anode sealing frame are bonded together to form a fluid seal. The fluid barrier may be a metal and may be selected from, for example, titanium, stainless steel, nickel, tantalum, niobium, and alloys thereof. The fluid barrier may be plated with a metal
10 selected, for example, from gold, silver, copper, platinum, and combinations thereof. Alternately the fluid barrier may be an electrically conductive non-metal, such as a conductive polymer or metal filled polymer.

The frames and flow fields are similar to those discussed above. However, the frames in this embodiment are not formed around the fluid barrier. Instead, a cathode
15 sealing frame and an anode sealing frame are separately formed as above, and then the cathode sealing frame and the anode sealing frame are bonded on either side of the gas barrier by a method selected from heat welding, chemical welding, adhesives, and combinations thereof. Alternatively, gaskets may be used to create a fluid tight seal between the cathode and anode sealing frames. The gaskets suitable for use may include,
20 for example, o-rings, gaskets incorporated into one of the sealing frames, and gaskets applied by print screening.

The fluid barrier may not extend to the components. Rather the fluid barrier may overlap the anode sealing frame and the cathode sealing frame only a sufficient amount to create a fluid-tight seal.

25 Another embodiment of the present invention includes a fluid cooled bipolar plate comprising a cathode fluid barrier, an anode fluid barrier, an anode sealing frame adapted to receive a perimeter of an anode side of the anode fluid barrier, a cathode sealing frame adapted to receive a perimeter of a cathode side of the cathode fluid barrier, a cooling frame adapted to receive a perimeter of a cathode side of the anode fluid barrier and a
30 perimeter of the anode side of the cathode fluid barrier, wherein an anode side of the cooling frame is bonded to the anode frame to form a fluid seal and the cathode side of

the cooling frame is bonded to the cathode frame to form a fluid seal. The fluid barrier may be a metal and may be selected from, for example, titanium, stainless steel, nickel, tantalum, niobium, and alloys thereof. The fluid barrier may be plated with a metal selected, for example, from gold, silver, copper, platinum, and combinations thereof.

5 Alternately the fluid barrier may be an electrically conductive non-metal, such as a conductive polymer or metal filled polymer. The fluid barriers may be made of different materials.

The bipolar plate may further include the anode side of the anode fluid barrier having an anode flow field, the cathode side of the cathode fluid barrier having a cathode

10 flow field, and a cooling flow field parallel to and between the cathode fluid barrier and the anode fluid barrier. The anode flow field and the cathode flow field may be attached to the fluid barriers before the cathode sealing frame and the anode sealing frame are bonded to the cooling frame or alternatively afterwards. The flow fields may be attached by methods selected from, for example, adhesives, sintering, soldering and combinations

15 thereof.

The sealing frames and flow fields are formed as previously discussed. The sealing frames may be bonded by methods selected from, for example, heat welding, chemical welding, adhesives, and combinations thereof. Casketing surfaces may be used to create fluid tight seals between components that are not otherwise bonded. As above,

20 the anode fluid barrier overlaps the anode sealing frame and the cathode fluid barrier overlaps the cathode sealing frame only a sufficient amount to create a fluid-tight seal.

A method for assembling the bipolar plate of the present invention is also included. The steps provide inserting a perimeter of the gas barrier into a mold and injecting a polymer into the mold. The method further includes bonding an anode flow

25 field onto an anode side of the fluid barrier and bonding a cathode flow field onto a cathode side of the fluid barrier.

A method for assembling the fluid cooled bipolar plate is also provided. The method provides adapting the cathode sealing frame and the anode sealing frame to receive a perimeter of the gas barrier, aligning the cathode sealing frame and the anode

30 sealing frame around the perimeter of the gas barrier, bonding the cathode sealing frame to the anode sealing frame, wherein the bond creates a fluid tight seal.

The foregoing and other objects, features and advantages of the invention will be apparent from the following more particular description of a preferred embodiment of the invention, as illustrated in the accompanying drawing wherein like reference numbers represent like parts of the invention.

5

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 illustrates one pattern that may be chemically etched into a fluid barrier to create a flow field.

FIG. 2 is a top view of a bipolar plate having the sealing frame formed around the fluid barrier in accordance with the present invention.

10

FIG. 3 is a cross-sectional view of the bipolar plate illustrated in FIG. 2.

FIG. 4 is an exploded view of a bipolar plate assembled with a cathode sealing frame and an anode sealing frame in accordance with the present invention.

15

FIG. 5 is an exploded view of a fluid cooled bipolar plate assembled with a cathode sealing frame, an anode sealing frame and a cooling sealing frame in accordance with the present invention.

FIG. 6A-E illustrates a method for making a bipolar plate having a sealing frame formed around the fluid barrier in accordance with the present invention.

20

FIG. 7A-D illustrates a method form making a bipolar plate with a cathode sealing frame and an anode sealing frame in accordance with the present invention.

DETAILED DESCRIPTION

25

The present invention provides a bipolar plate for use in an electrochemical cell stack comprising a fluid barrier and a sealing frame that is formed around and overlaps the perimeter of the fluid barrier. The sealing frame is formed around the fluid barrier by, for example, placing the fluid barrier in a mold and then injecting a polymer into the mold, thereby forming the sealing frame around the fluid barrier such that the sealing frame overlaps the perimeter of the fluid barrier. Because there are no surfaces to seal between the perimeter of the fluid barrier and the sealing frame, gaskets or other sealing surfaces are not required, thereby providing a slimmer and lighter bipolar plate having fewer parts to assemble.

30

The present invention further provides a bipolar plate comprising a fluid barrier having the perimeter of the fluid barrier between a preformed cathode sealing frame and an anode sealing frame. In this embodiment, the anode and cathode sealing frames are adapted to receive an overlapped portion of the perimeter of the fluid barrier. The anode and cathode sealing frames are then bonded together to form a fluid tight seal.

In yet another embodiment, the present invention provides a cooled bipolar plate comprising a cathode fluid barrier, an anode fluid barrier, and three sealing frames: the anode sealing frame, the cathode sealing frame, and the cooling sealing frame. In the cooled bipolar plate, a cooling fluid, such as water, is circulated between the two fluid barriers, carrying excess heat away from the electrochemical cell. Alternatively, a heating fluid may be circulated between the two fluid barriers to heat the electrochemical cell rather than to cool it. The anode sealing frame is bonded to the anode side of the cooling frame, overlapping the perimeter of the anode fluid barrier. The cathode sealing frame is bonded to the cathode side of the cooling frame, overlapping the perimeter of the cathode fluid barrier.

The sealing frames may be made from a polymer selected from, for example, thermoplastics, thermosets, reactive sets and combinations thereof. The polymer may be selected from polyvinylidene fluoride, polyvinylidene difluoride, polytetrafluoroethylene, polyamides, polysulfone, polyetherketones, polycarbonate, polypropylene, polyimides, polyurethanes, epoxies, silicones, and combinations thereof. These polymers are all non-conductive so that the sealing frames are non-conductive when made from these polymers.

Optionally, the polymers used to form the sealing frames may be mixed with one or more fillers. The fillers may be added to modify the performance of the polymer, act as a diluent, or combinations thereof. The filler may be, for example, organic polyamide fibers, which improves the strength of the frames.

The sealing frame may be formed by a method selected from, for example, injection molding, compression molding and other methods known to those having ordinary skill in the art. The sealing frames may also include other features, such as alignment pins, alignment holes, reinforcing liners for fluid passages, fluid manifolds and combinations thereof. These features may be included in the mold design, thereby

allowing the features to be formed in the sealing frames during the molding process. Alternatively, a sealing frame may be machined from a block of the polymer. Furthermore, some of the features, such as alignment holes and manifolds, may be machined or drilled into the sealing frames after the sealing frames have been formed.

5 The fluid barriers are preferably conductive so that the fluid barriers may transport electrons as part of the electrical circuit formed through the electrochemical cells. The fluid barrier may be a conductive graphitic material. The fluid barrier is preferably a metal. The fluid barriers may be made from a metal selected from titanium, stainless steel, nickel, tantalum, niobium, and alloys thereof. Optionally, the fluid
10 barriers may be plated with a second metal. The plating metal may be selected from gold, platinum, silver, copper, and combinations thereof.

Preferably the fluid barriers do not extend to the outer perimeter of the sealing frame. The channels, manifolds, alignment holes, alignment pins and other similar features of the sealing frames may all be located beyond the overlapped perimeter of the
15 fluid barrier. Preferably, the sealing frame overlaps the fluid barrier perimeter just sufficiently to allow the formation of a fluid tight seal. There are two advantages associated with minimizing the overlap between the fluid barrier and the sealing frames. First, because there is less material used to form the smaller fluid barrier, the weight of the fluid barrier and hence, the weight of the bipolar plate is reduced. Secondly, the fluid
20 barrier does not have to be drilled or machined to form the additional features found in the sealing frames such as, for example, the fluid channels, manifolds, and alignment pins.

Optionally a retaining band may be provided around the outer perimeter of the sealing frames. The optional retaining band provides hoop stress reinforcement to insure
25 pressure containment if pressure containment is a requirement for a particular application.

The bipolar plate of the present invention may also provide an anode flow field and a cathode flow field. The flow fields may be bonded to the bipolar plate before the sealing frame surrounds the fluid barrier. The flow fields may be bonded to the bipolar plate by methods known to those having ordinary skill in the art. Such methods may
30 include, for example, adhesives, soldering, sintering and combinations thereof. Information on bonding flow fields to fluid barriers and assembling bipolar plates and

electrochemical cell stacks is fully disclosed by Cisar, *et al.*, in U.S. Patent No. 6,146,780, which is hereby fully incorporated herein by reference. Alternatively, the flow fields may be etched into the fluid barrier by chemical etching using a photo-imaged pattern, thereby producing a gas barrier with flow fields from a single piece of metal.

5 FIG. 1 illustrates one pattern that may be chemically etched into a fluid barrier using a photo-imaged pattern to create a flow field. The pattern illustrated in FIG. 1 has been found to offer an excellent combination of maximizing electrical contact, minimizing gas flow resistance, and minimizing part weight.

10 Flow fields bonded to the fluid barrier may be formed from material selected from expanded metal mesh, metal foam, conducting polymer foam, porous conductive carbon material and combinations thereof.

An anode flow field may be attached to or formed on the anode side of a gas barrier and a cathode flow field may be attached to or formed on the cathode side of a fluid barrier. For a fluid cooled bipolar plate, having an anode fluid barrier and a cathode fluid barrier that form a cooling fluid chamber between them, a cooling flow field may be
15 attached or formed on either the cathode fluid barrier or the anode fluid barrier on the cooling chamber side of the fluid barrier.

The bipolar plate of the present invention, having the sealing frame formed around and overlapping the perimeter of the fluid barrier, is thinner than a conventional
20 bipolar plate. The gaskets required by a conventional bipolar plate, to seal between the fluid barrier and the sealing frames, add thickness to the assembled conventional bipolar plate. Since these gaskets are not required by the bipolar plate having the sealing frame formed around and overlapping the perimeter of the fluid barrier, bipolar plate of the present invention may be much thinner, subject only to the thickness required to provide
25 flow fields deep enough to allow the fluids to pass through the flow fields without unacceptable pressure drops. Furthermore, the width of the sealing frame of the present invention may be reduced because the sealing areas required for the gaskets of the conventional bipolar plate are not required. This further reduces the weight of the bipolar plate.

30 FIG. 2 is a top view of a bipolar plate having the sealing frame formed around the fluid barrier in accordance with the present invention. The bipolar plate 10 comprises the

fluid frame 11 that is formed around the fluid barrier 15. An anode flow field 12 is shown attached to the fluid barrier 15. Fluid manifolds 13 allow reactant fluids and products to flow to and from the electrochemical cells forming the electrochemical cell stack. Alignment holes 14 are also shown that may be used to properly align the bipolar plate during the electrochemical cell stack assembly.

FIG. 3 is a cross-sectional view of the bipolar plate illustrated in FIG. 2. As may be seen in FIG. 3, the sealing frame 11 is formed around the fluid barrier 15. The fluid barrier 15 does not extend to the manifolds 13 but only extends far enough into the sealing frame to form a fluid seal. The anode flow field 12 is attached to the anode side of the fluid barrier 15 and the cathode flow field 16 is attached to the cathode side of the fluid barrier 15. Gasket surfaces 17 are optionally incorporated into the sealing frame 11 and may be produced by a screen-printing process prior to assembly of the electrochemical cell stack.

FIG. 4 is an exploded view of a bipolar plate assembled with a cathode sealing frame and an anode sealing frame in accordance with the present invention. A cathode sealing frame 22 and an anode sealing frame 21 may be formed, for example, by injection molding, compression molding or machined from a block of solid polymer. An anode flow field 12 and a cathode flow field 16 are attached to the fluid barrier 15. Gasket surfaces 17 are optionally incorporated into the sealing frames 21, 22 and may be produced by a screen-printing process prior to assembly of the electrochemical cell stack. The manifold 13 is used to transport reactant fluids and products to and from the electrochemical cell. After the anode seal frame 12 and the cathode seal frame 22 are placed around the fluid barrier 15, the mating surfaces 23 may be bonded together by, for example, adhesives, chemical welding, or laser welding.

FIG. 5 is an exploded view of a fluid cooled bipolar plate assembled with a cathode sealing frame, an anode sealing frame and a cooling sealing frame. The anode sealing frame 21, the cathode sealing frame 22 and the cooling sealing frame 25 may be formed, for example, by injection molding, compression molding or machined from a block of solid polymer. An anode flow field 12 is attached to the anode side of the anode fluid barrier 26. A cooling flow field 28 is attached to the cooling side of the anode fluid barrier 26. A cathode fluid barrier 27 is parallel to the anode fluid barrier 26 and a

cathode flow field 16 is attached to the cathode side of the cathode fluid barrier 27. Gasket surfaces 17 are optionally incorporated into the sealing frames 21, 25, 22 and may be produced by a screen-printing process prior to assembly of the electrochemical cell stack. The manifold 13 is used to transport reactant fluids and products to and from the electrochemical cell. After the anode seal frame 21 and the cooling seal frame 22 are placed around the anode fluid barrier 26, the mating surfaces 23 may be bonded together by, for example, adhesives, chemical welding, or laser welding. Likewise, after the cathode sealing frame 22 and the cooling sealing frame 25 are placed around the cathode fluid barrier 27, the mating surfaces 23 may be bonded together by, for example, adhesives, chemical welding, or laser welding.

FIGS. 6A-E illustrate a method for making a bipolar plate having a sealing frame formed around the fluid barrier in accordance with the present invention. FIG. 6A illustrates the step of providing a fluid barrier 15 having an anode flow field 12 attached to the anode side of the fluid barrier 15 and having a cathode flow field 16 attached to the cathode side of the fluid barrier 15. FIG. 6B illustrates a second step of inserting the fluid barrier 15 into a mold 41. The mold 41 has a solid piece 42 that forms a manifold in the completed sealing frame. In FIG. 6C, the mold 41 is closed, with a sufficient portion of the fluid barrier 15 being within the mold 41 to provide a seal between the sealing frame and the fluid barrier 15. In FIG. 6D, polymer 43 is injected into the mold. In FIG. 6E, the polymer 43 has solidified and the bipolar plate 10 removed from the mold 41 having formed the sealing frame 11 with the manifold 13. Optionally, gasket surfaces 17 are incorporated into the sealing frame 11, produced by a screen-printing process.

FIGS. 7A-D illustrate a method for making a bipolar plate with a cathode sealing frame and an anode sealing frame in accordance with the present invention. FIG. 7A illustrates the step of providing a fluid barrier 15 having an anode flow field 12 attached to the anode side of the fluid barrier 15 and having a cathode flow field 16 attached to the cathode side of the fluid barrier 15. FIG. 7B illustrates the step of providing an anode sealing frame 21 and a cathode sealing frame 22 having a manifold 13 as required by an electrochemical cell stack. The sealing frames may be produced by a method selected from injection molding, compression molding, machining and combinations thereof. The anode sealing frame 21 has a lip 45 that receives the fluid barrier 15. Optionally, gasket

surfaces 17 produced by a screen-printing process are incorporated into the sealing frames 21, 22. FIG. 7C illustrates the step of inserting the fluid barrier 15 into the lip 45 and aligning the sealing frames 21, 22 so that the manifolds 13 are properly aligned. Optionally, a laser absorber layer 46 may be applied to the cathode sealing frame to
5 absorb the laser light used in the laser welding procedure. FIG. 7D illustrates the step of welding the sealing frames 21, 22 together with a laser welder, the laser 47 being absorbed by the laser absorber layer to melt the polymer frames 21,22, thereby bonding the frames 21,22 together.

It will be understood from the foregoing description that various modifications
10 and changes may be made in the preferred embodiment of the present invention without departing from its true spirit. It is intended that this description is for purposes of illustration only and should not be construed in a limiting sense. The scope of this invention should be limited only by the language of the following claims